KEPSTAN® PEKK resin is a high performance thermoplastic material, based on PolyEtherKetoneKetone (PEKK) highly stable chemical backbone. Its semi crystalline structure in solid state offers an outstanding combination of mechanical and thermal strength together with chemical and fire resistance.

KEPSTAN® 8010C30 is a carbon fiber reinforced compound, based on the 8000 series of KEPSTAN® resins. This series offers the highest alass transition temperature and the highest crystallinity, leading to the best tensile and compression strengths among the different series of KEPSTAN® PEKK copolymers.

**KEPSTAN® 8010C30** is a low flow grade, suitable for extrusion, compression and injection molding.

KEPSTAN® 8010C30 is available in pellet form, and standard packaging is 10 kg boxes.

## MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	18	cm <sup>3</sup> /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-
MECHANICAL PROPERTIES			
Charpy Impact Strength, +23°C	34	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	6	kJ/m²	ISO 179/1eA
OTHER PROPERTIES			
Density	1450	kg/m³	ISO 1183

Drying temperature and time: 120°C for 6 to 8 hours

Processing temperature: 370 – 380°C

Temperature settings - Injection: Rear 350°C / Center 375°C / Front 370°C / Nozzle 385°C Mold temperature (to facilitate filling of the cavity and polymer crystallization): 230 - 240°C Temperature settings - Extrusion: Zones 1/2/3/4: 355°C/ 370°C/ 385°C/ 385°C Die: 370°C

## **PROCESSING**

Injection Molding, Profile Extrusion

## **DELIVERY FORM**

Pellets

## **REGIONAL AVAILABILITY**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/en/products/product-safety/disclaimer/index.html

Kepstan® is a registered trademark of Arkema © 2022 Arkema Inc. All rights reserved.

Arkema Inc. - Technical Polymers 900 First Avenue King of Prussia, PA 19406

Tel.: +1 610 205 7000 Fax: +16102057497arkema-americas.com

Headquarters: Arkema France arkema.com

420. rue d'Estienne d'Orves 92705 Colombes Cedex — France Tel.: +33 1 49 00 80 80 Fax: +33149008396